

# Synthesis and Characterization of Nano-structured ABo<sub>3</sub>

Sumit Kumar Gupta<sup>\*1</sup> and Rachana Sharma<sup>2</sup>

Assistant Professor Parishkar College of Global Excellence, India<sup>1</sup>

Research scholar Sunrise University, India<sup>2</sup>

## ABSTRACT

Nanoparticles of ABo<sub>3</sub> (A= Ba, Sr & Ca; B=Zr) have been synthesized using modified single step combustion method for the first time. All the peaks of the XRD are indexed and no peaks are observed other than the expected peaks of the respective nanopowders. The analysis results show that they are isostructural and no trace of any impurities. Only the as-prepared powder of CaZrO<sub>3</sub> needs an annealing of about 700 °C for 1 h. Their lattice parameters are agreed well with JCPDS values. In this paper r, the preparation and property analysis have been planned for single perovskites barium zirconate, strontium zirconate using a modified single-step auto-igniting combustion process.

**Keywords:** XRD; SEM; TEM; Ethylene Diamine Tetra Acetic acid (EDTA); Perovskite materials; Debye Scherrer's Formula; EDX

\*Correspondence to: Sumit Kumar Gupta, Assistant Professor Parishkar College of Global Excellence, India

Received: Feb 07, 2022; Accepted: Apr 15, 2022; Published: Apr 20, 2022

Citation: Gupta SK and Sharma R (2022) Synthesis and Characterization of Nano-structured ABo<sub>3</sub>. J Nanomed Nanotech Nanomat. 3: 115.

Copyright: ©2022 Gupta SK, et al. This is an open-access article distributed under the terms of the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original author and source are credited.

## INTRODUCTION

The successful synthesis of large-scale nanostructured materials with grain sizes in the range of 10-200 nm represents a major achievement in the emerging field of nanotechnology. The scientific literature indicates that there are many techniques that can be used to produce nanostructured materials, including inert gas condensation or chemical vapor condensation [1,2] pulse electron deposition [3], plasma synthesis [4], crystallization of amorphous solids [5], severe plastic deformation [6], and consolidation of mechanically alloyed or cryomilled powders [7]. However, only a few of these techniques, such as electrodeposition [8] and consolidation of mechanically alloyed/cryomilled powders [9], generate nanostructures with sufficient thermal stability to permit the fabrication of bulk materials. Water, a natural solvent is known to exhibit unique properties under supercritical conditions and this has been suitably exploited to promote dissolution, diffusion, adsorption, reaction rate, nucleation and growth for the synthesis of ceramics [10]. Over the past decade, hydrothermal synthesis [11] has been widely used to produce weakly aggregated fine powders of both binary and mixed oxides under mild conditions [6-10]. There is also considerable interest in the synthesis of oxide materials via microwave heating both at atmospheric pressure and under hydrothermal conditions, which notably accelerates chemical reactions [12]. In combustion synthesis, the exothermicity of the redox (reduction-oxidation or electron transfer) chemical

reaction is used to produce useful materials. By controlling the processing parameters such as microwave initiation, gravity, precursors and additives to redox mixtures, it has been possible to obtain nano size oxides using combustion synthesis. In this paper r, the preparation and property analysis have been planned for single perovskites barium zirconate, strontium zirconate and calcium zirconate using a modified single-step auto-igniting combustion process


## SYNTHESIS OF NANOCRYSTALLINE ABo<sub>3</sub>

To produce powders of high phase purity, repeated grinding and re-firing is necessary to sufficiently complete the solid-state reaction of BaCO<sub>3</sub> and ZrO<sub>2</sub>. BaZrO<sub>3</sub> is a highly refractory material, and extended mechanical grinding is typically required to sufficiently reduce the particle size to allow sintering to high density [13]. For present investigations, nanoparticles of ABo<sub>3</sub> (A=Ba, Sr & Ca; B=Zr) have been synthesized using a modified single step combustion process. An aqueous solution containing ions of A (A=Ba, Sr & Ca) and Zr was prepared by dissolving stoichiometric amount of high purity A(NO<sub>3</sub>)<sub>2</sub> (99%, CDH, India) and ZrOC<sub>12</sub>·8H<sub>2</sub>O (99%, CDH, India) in 200ml distilled water in a glass beaker. Citric acid (99%, CDH, India) was then added to the solution containing A (A=Ba, Sr & Ca) and Zr ions. Amount of citric acid was calculated based on total valence of the oxidizing and reducing

agents for maximum release of energy during combustion [14]. In the preparation of nanoparticles of other ceramic oxides using combustion process [15], polyvinyl alcohol and urea were used as the complexing agent and fuel, respectively. In these cases, usual calcinations of the combustion product were essential to get a single phase nano material. In the present combustion method, citric acid was used as the complexing agent instead of polyvinyl alcohol and urea was replaced with ammonia. Using this complexing agent and oxidant fuel system, it was possible to get a single phase  $AZrO_3$ .

### CHARACTERIZATION OF THE STRUCTURE AND PHASE PURITY OF $ABO_3$ USING X-RAY DIFFRACTION TECHNIQUE

As-prepared  $AZrO_3$  ( $A=Ba, Sr \& Ca$ ) powder obtained by the combustion method is characterized by different characterization techniques. The structure and phase purity of the powders are examined by powder X-ray diffraction (XRD) technique using X-ray Diffractometer.



**Figure 1:** The XRD pattern of as-prepared  $BaZrO_3$  nanocrystals. A close-up view of (110) predominant peak in the inset is used to calculate the grain size of the powder


Peak Position ( $2\theta$ )	(hkl)	Interplanar Distance ( $d_{hkl}$ ) (Å)	Deviation in $d_{hkl}$ ( $\Delta d_{hkl} = d_o - d_s$ )	Microstrain
21.1539	(100)	4.196415	0.00195	0.000472
29.1843	(110)	5.136412	-0.00475	-0.00228
36.1722	(111)	3.16423	-0.00425	-0.0018
42.1918	(200)	2.14569	-0.00324	-0.00202
52.3877	(211)	1.24587	0.002038	-0.00423
61.6038	(220)	1.12356	0.000112	-0.00302

**Table 1:** Interplanar  $d_{hkl}$  spacings and microstrain in the  $BaZrO_3$  nanopowder.


Peak Position ( $2\theta$ )	(hkl)	Interplanar Distance ( $d_{hkl}$ ) (Å)	Deviation in $d_{hkl}$ ( $\Delta d_{hkl} = d_o - d_s$ )	Microstrain
20.1539	(020)	3.196413	0.00175	0.000272
28.1843	(111)	4.136512	-0.00375	-0.00218
35.1721	(002)	2.15423	-0.00325	-0.00018
40.1914	(040)	2.13569	-0.00224	0.001436
42.3855	(240)	1.12587	0.001038	0.002674
64.6038	(242)	1.13156	0.000111	-0.00017

**Table 2:** Interplanar  $d_{hkl}$  spacings and microstrain in the  $BaZrO_3$  nanopowder.


shows the X-ray diffraction pattern of as-prepared and annealed at 600°C powders of SrZrO<sub>3</sub> for 28 between 20° and 60°.



**Figure 2:** The XRD pattern of as-prepared and annealed SrZrO<sub>3</sub> nanocrystals at 600 °C.



**Figure 3:** SEM Image of Sintered Pellet of BaZrO<sub>3</sub> Sintered at 1650°C.



**Figure 4:** The Scanning Electron Microscopic Studies on the SrZrO<sub>3</sub> Sintered Sample.

## CONCLUSION

Nanoparticles of AB<sub>3</sub> (A = Ba, Sr & Ca; B=Zr) have been synthesized using modified single step combustion method for the first time. All the peaks of the XRD are indexed and no peaks are observed other than the expected peaks of the respective nanopowders. The analysis results show that they are isostructural and no trace of any impurities. Only the as-prepared powder of CaZrO<sub>3</sub> needs an annealing of about 700 °C for 1 h. Their lattice parameters are agreed well with JCPDS values. While annealing the SrZrO<sub>3</sub> sample to 600 °C, the crystallinity increases. The scanning electron micrographs reveal a very homogeneous microstructure without agglomerates or exaggerated grain growth. There are no pores which signify the enhancement of density. Fine crystalline nature is observed in transmission electron micrographs.

## REFERENCES

1. Mahon SW, Cochrane RF, Howson MA (1996) GMR and precipitation kinetics in mechanically alloyed Cu<sub>90</sub>Co<sub>10</sub>. Nanostructured materials, Nanostruct Mater 7: 195-204.
2. Manik SK, Pradhan SK (2005) X-ray microstructure characterization of ball-milled nanocrystalline microwave dielectric CaZrO<sub>3</sub> by Rietveld method. J Appl Cryst 38: 291-298.

3. Manik SK, Pradhan SK (2005) X-ray microstructure characterization of ball-milled nanocrystalline microwave dielectric  $\text{CaZrO}_3$  by Rietveld method. *J Appl Cryst* 38: 291-298.
4. Mao YB, Banerjee S, Wong SS (2003) Hydrothermal synthesis of perovskite nanotubes. *Chem Comrn* 3: 408-409.
5. Mao YB, Banerjee S, Wong SS (2003) Large-scale synthesis of single-crystal line perovskite nanostructures. *J Am Chem Soc* 125: 15718-15719.
6. Cahay M (1994) Semiconductor Quantum Devices. *Phys Acad Press* 89:93.
7. Maruyama T, Shionoya J (2021) Zinc oxide thin films prepared by chemical vapor deposition from zinc acetate. *J Mater Sci Lett* 11: 170-172.
8. Park HK, Han YS, Kim DK, Kim CH (1998) Synthesis of  $\text{LaCrO}_3$  powders by microwave induced combustion of metal nitrate-urea mixture solution. *J Mater Sci Lett* 17: 785-787.
9. Park S, Vohs JM, Gorte RJ (2000) The Direct Oxidation of Hydrocarbons in a Solid Oxide Fuel Cell. *Nature* 404: 265-267.
10. Patil KC, Aruna ST, Ekambaram E (1997) Combustion synthesis. *Curr Opin Solid State Mater Sci* 2: 158-165.
11. Patil KC, Aruna ST, Mimani T (2002) Combustion synthesis: an update. *Curr Opin Solid State Mater Sci* 6: 507-512.
12. Patil KC, Mimani T (2000) Preparation and properties of nanocrystalline magnetic oxides. *Mag Soc India Bull* 22: 21-26.
13. Patil KC, Radhakrishnan S, Pethkar S, Vijayamohan K (2001) Piezoresistivity of conducting polyaniline/ $\text{BaTiO}_3$  composites. *J Mat Res* 16: 1982-1988.
14. Patnaik P (2004) *Dean's Analytical Chemistry Handbook*. 2nd ed McGraw-Hill.